

Multilayer interference pigment with transparent central layer

Patent Number: ☐ US6156115
Publication date: 2000-12-05
Inventor(s): FRIZ MARTIN (DE); PFAFF GERHARD (DE); BAUER GERD (DE); KUNTZ MATTHIAS (DE); SCHANK CHRISTINA (DE)
Applicant(s):: MERCK PATENT GMBH (DE)
Requested Patent: ☐ DE19707806
Application Number: US19980171803 19981026
Priority Number(s): DE19971007806 19970227; WO1998EP00930 19980218
IPC Classification: C09C1/00 ; C09C1/04 ; C09C1/22 ; C09C1/24 ; C09C1/36
EC Classification: C09C1/00F, C09D5/36
Equivalents: BR9805917, CN1217735, CZ9803358, ☐ EP0912641 (WO9838254), JP2000511968T, ☐ WO9838254

Abstract

PCT No. PCT/EP98/00930 Sec. 371 Date Oct. 26, 1998 Sec. 102(e) Date Oct. 26, 1998 PCT Filed Feb. 18, 1998 PCT Pub. No. WO98/38254 PCT Pub. Date Sep. 3, 1998 Multilayer interference pigment consisting of a central layer of a transparent or semitransparent material of low refractive index and alternating layers of a metal or of a material of high refractive index and of a material of low refractive index either side of the central layer, the material of low refractive index preferably being magnesium fluoride or acrylate and the metal preferably being aluminium or chromium.

Data supplied from the esp@cenet database - I2